

REPORT DOCUMENTATION PAGE				Form Approved OMB No. 0704-0188	
1a. REPORT SECURITY CLASSIFICATION Unclassified			1b. RESTRICTIVE MARKINGS		
2a. SECURITY CLASSIFICATION AUTHORITY			3. DISTRIBUTION / AVAILABILITY OF REPORT APPROVED FOR PUBLIC RELEASE; DISTRIBUTION UNLIMITED		
2b. DECLASSIFICATION / DOWNGRADING SCHEDULE			5. MONITORING ORGANIZATION REPORT NUMBER(S)		
4. PERFORMING ORGANIZATION REPORT NUMBER(S) BRL-TR-2952			7a. NAME OF MONITORING ORGANIZATION		
6a. NAME OF PERFORMING ORGANIZATION US Army Ballistic Research Laboratory		6b. OFFICE SYMBOL (If applicable) SLCBR-IB	7b. ADDRESS (City, State, and ZIP Code)		
6c. ADDRESS (City, State, and ZIP Code) Aberdeen Proving Ground, MD 21005-5066			9. PROCUREMENT INSTRUMENT IDENTIFICATION NUMBER		
8a. NAME OF FUNDING / SPONSORING ORGANIZATION		8b. OFFICE SYMBOL (If applicable)	10. SOURCE OF FUNDING NUMBERS		
8c. ADDRESS (City, State, and ZIP Code)			PROGRAM ELEMENT NO. 61102A	PROJECT NO. AH43	TASK NO.
11. TITLE (Include Security Classification) DECOMPOSITION AND STABILITY STUDIES OF TAGN					
12. PERSONAL AUTHOR(S) P.J. Kaste, F. Volk, R. Jacob, F. Nagel, B. Schon, T. Wohlhaupter					
13a. TYPE OF REPORT Final		13b. TIME COVERED FROM Dec 86 TO Jun 87		14. DATE OF REPORT (Year, Month, Day)	
15. PAGE COUNT					
16. SUPPLEMENTARY NOTATION					
17. COSATI CODES			18. SUBJECT TERMS (Continue on reverse if necessary and identify by block number)		
FIELD	GROUP	SUB-GROUP	TAGN (Triaminoquanidinium Nitrate), DAGN (Diaminoquanidinium Nitrate), Thermal Analysis, Mass Spectrometry, RDX (Trinitrotriazacyclohexane), Decomposition Chemistry		
19	01				
07	03				
19. ABSTRACT (Continue on reverse if necessary and identify by block number)					
<p>The thermal decomposition of TAGN is of interest for understanding its stability and compatibility with other nitramine propellant ingredients. Low vulnerability (LOVA) propellants containing inert polymers such as hydroxy-terminated polybutadiene or the cellulose acetate polymers and the nitramines HMX or RDX have been formulated at ICT. We are interested in determining the effect of TAGN on the stability of these propellants by studying their thermal decomposition at temperatures below the deflagration temperature (<220°C).</p> <p>In this paper the preliminary results for this study are presented. Techniques used include thermal decomposition/MS, in which the evolved gases are analyzed by mass spectroscopy. The solid residue was analyzed by Fourier transform infrared spectroscopy (FTIR), elemental (carbon, hydrogen and nitrogen) analysis, thin layer chromatography, differential scanning calorimetry and atomic absorption spectroscopy. The results from the analyses agree and</p>					
20. DISTRIBUTION / AVAILABILITY OF ABSTRACT <input type="checkbox"/> UNCLASSIFIED/UNLIMITED <input checked="" type="checkbox"/> SAME AS RPT. <input type="checkbox"/> DTIC USERS			21. ABSTRACT SECURITY CLASSIFICATION Unclassified		
22a. NAME OF RESPONSIBLE INDIVIDUAL DR. PAMELA J. KASTE			22b. TELEPHONE (Include Area Code) 301-278-6168		22c. OFFICE SYMBOL SLCBR-IB-I

19. Abstract (Cont'd):

indicate that ammonia and nitrogen are the chief gases evolved and that the residue remains enriched in nitrate.

We have also investigated the difference between pink and pure TAGN crystals using FTIR spectroscopy. Although infrared spectroscopy had been previously used to study TAGN, no differences in the pink and pure samples were seen. In this work, pink TAGN and red crystals recovered from recrystallization of the pink material suggest that the pink TAGN is enriched with the nitrated functionality. The identity of this nitrate product is under investigation.

LIBRARY
RESEARCH REPORTS DIVISION
NAVAL POSTGRADUATE SCHOOL
MONTEREY, CALIFORNIA 93940

TECHNICAL REPORT BRL-TR-2952 .

BRL

1938 - Serving the Army for Fifty Years - 1988

copy
DECOMPOSITION AND STABILITY STUDIES OF TAGN

by PAMELA J. KASTE *and others*
F. VOLK
R. JACOB
F. NAGEL
B. SCHON
T. WOHLHAUPTER

DECEMBER 1988 .

APPROVED FOR PUBLIC RELEASE; DISTRIBUTION UNLIMITED.

U.S. ARMY LABORATORY COMMAND

BALLISTIC RESEARCH LABORATORY.
//
ABERDEEN PROVING GROUND, MARYLAND

DESTRUCTION NOTICE

Destroy this report when it is no longer needed. DO NOT return it to the originator.

Additional copies of this report may be obtained from the National Technical Information Service, U.S. Department of Commerce, Springfield, VA 22161.

The findings of this report are not to be construed as an official Department of the Army position, unless so designated by other authorized documents.

The use of trade names or manufacturers' names in this report does not constitute indorsement of any commercial product.

TABLE OF CONTENTS

	<u>Page</u>
LIST OF FIGURES.....	5
I. INTRODUCTION.....	7
II. EXPERIMENTAL.....	7
III. THERMAL DECOMPOSITION/MASS SPECTROMETRIC ANALYSIS.....	8
IV. FTIR RESULTS.....	9
V. ATOMIC ABSORPTION ANALYSIS.....	14
VI. C, H, N, AND O ANALYSIS.....	16
VII. DIFFERENTIAL SCANNING CALORIMETRY (DSC).....	16
VIII. THIN LAYER CHROMATOGRAPHY (TLC).....	22
IX. CONCLUSIONS.....	22
REFERENCES.....	25
DISTRIBUTION LIST.....	27

LIST OF FIGURES

<u>Figure</u>		<u>Page</u>
1	Infrared Spectra of the Tri-, Di-, Mono-Amino and Unsubstituted Guanidine Nitrates.....	10
2	Comparison of the Infrared Spectra of a TAGN Decomposition/ Condensate Product and DAGN.....	12
3	Infrared Spectra of the Solid Decomposition Products of TAGN Heated to 210-220°C.....	13
4	Infrared Spectra of the Recrystallization Liquor (After Concentration) of TAGN.....	15
5	Differential Scanning Calorimetry Analysis of TAGN.....	18
6	Differential Scanning Calorimetry Analysis of (a) the Solid Decomposition Residue of TAGN and (b) DAGN.....	19
7	DSC Analysis of (a) RDX and (b) a 1:1 Mixture of RDX and TAGN...	21
8	Thin Layer Chromatographic Separation of TAGN Decomposition Products.....	23

I. INTRODUCTION

Triaminoguanidium nitrate (TAGN) is of interest for a variety of RDX-based propellant applications such as low vulnerability (LOVA) propellant materials, gas generators and very high burning rate formulation. Its advantages include low molecular weight gas products and therefore low flame temperatures, as well as an increased muzzle velocity and impetus. Several reports have been published in which these advantages have been realized in ballistic measurements.¹⁻⁴ However, one critical disadvantage is the instability of TAGN, both alone and in propellant formulations. Colored (particularly pink) crystals of TAGN are commonly formed in the synthesis, storage and/or processing of TAGN. Care must be taken to avoid metal ion contamination and to ensure prompt solvent removal (particularly ethyl acetate, acetone, alcohols and those which are basic). However, even when such precautions are taken, the resultant TAGN often becomes discolored and problems with the propellants made from it are likely. In this laboratory differences in the physical appearance of propellants synthesized from pure TAGN versus an impure, pink TAGN were seen; a decrease in ballistic properties was also observed.⁵ It has also been found that the addition of NC to propellant formulations can reduce the stability of TAGN propellants and that the presence of a stabilizer such as ascardite can minimize the loss of stability in NC/TAGN formulations.⁶

The purpose of this research was to study the decomposition of TAGN alone, as well as its effect on the family of cellulose acetate polymers. LOVA propellants consisting of cellulose acetate, RDX and TAGN have been produced and studied at ICT; therefore, the stability and compatibility of these propellant materials is of interest.

II. EXPERIMENTAL

TAGN was studied at temperatures below its deflagration point (227°C), both alone or in cellulose acetate mixtures using mass spectroscopy (MS). The sample was thermally decomposed in a controlled temperature bath and was connected to the MS vacuum chamber via a heated transfer line and valve. The evolved gases were quantitatively measured as a function of temperature while the non-volatile residue was analyzed by methods described below. The sample was placed in the bath at 150°C and heated at approximately 10°C/min to its final temperature, nominally between 190-220°C. The sample was held at the final temperature for 15 min and the gases collected in the vacuum chamber; after that time the high resolution mass spectrum was obtained. The temperature of the transfer lines and vacuum chamber were kept high enough so that species such as NH_3 and acetic acid did not condense.

Infrared spectra were obtained using a 20SX Nicolet Fourier transform infrared (FTIR) spectrometer with MCT detector. One hundred scans at nominally two wavenumber resolution were signal averaged. A Perkin Elmer 300 series atomic absorption spectrometer was used for the determination of metals. The standard conditions suggested in the instrument manual were used for the selection of source lamp, flame gas and detection wavelength. Under these conditions, detection limits (in ppm) were as follows: Fe (0.005), Cu (0.1), Ni (0.004), Zn (0.001), Cd (0.001), Cr (0.001).

Differential scanning calorimetry (DSC) was performed at a heating rate of 10°C/min using a Mettler 3000 Thermal Analysis system. Nominal 3 mg samples were placed into 4 mm diameter pans with crimped lids and a vent hole. The flow rate of gas over the sample was nominally 20 cc/min. TAGN and its decomposition products were determined qualitatively by thin layer chromatography (TLC). The best conditions found for their separation were silica TLC plates with acetone: 20% NH₄OH (98:2) as the eluting solvent.

III. THERMAL DECOMPOSITION/MASS SPECTROMETRIC ANALYSIS

The results for TAGN over the temperature range 190–220°C were rather similar, with ammonia (35–45%) and nitrogen (50–65%) as the chief products (Table 1). Other gases found in small amounts include CO (<2%), formaldehyde (<4%), NO (<1%), and possibly hydrazine (<2%). N₂O was found in small amounts (<1%), usually only at the higher temperatures (210–220°C), or if prolonged (30–60 min) heating periods were used. Unfortunately, no difference was seen between the gases evolved from the pink and pure TAGN.

Table 1. Mass Spectrometric Analysis of the Gaseous Decomposition Products of TAGN Alone and Mixtures with Cellulose Acetate Binders

	<u>NH₃</u>	<u>N₂</u>	<u>CO</u>	<u>CO₂</u>	<u>H₂C=O</u>	<u>NO</u>	<u>N₂O</u>
TAGN	35.	58.	<2	----	<4	<1	----
CA				100.			
TAGN/CA 75/25	3.8	58.8	3.6	16.7	---	5.6	10.6
TAGN/CAB	17.9	62.4	1.3	5.8	---	2.0	3.0

Note: H₂O was not included in the above analyses.
Decomposition temperature was 210–220°C.
Values are in mole percent.

Since the interaction between TAGN and cellulosic binders is of interest, a mixture of TAGN:CA was also studied in the MS under the conditions mentioned above. Cellulose acetate (CA) alone yielded no permanent gases at temperatures up to 220°C; only acetic acid was formed. However, the 1:1 by weight mixture yielded almost no NH₃ or acetic acid, but gave copious amounts of N₂O. Mixtures of TAGN with cellulose acetate butyrate (CAB) demonstrated the same effects; N₂O was observed in these mixtures as well. The NH₃ concentration in the mixture was lower than in the TAGN sample alone as well. The effect of N₂O production and decreased NH₃ level is less with CAB than with CA, presumably due to the lower acetate substitution in the CAB.

Although it was suspected that the NH₃ produced from TAGN might react with CA, it was surprising to find that so much ammonia was consumed (assuming that it was formed, as in TAGN alone) and that such a large quantity of N₂O was produced. In an attempt to determine what reactions might be involved in

the N_2O production, a mixture of TAGN and underivatized cellulose (no acetate groups present) was decomposed in the same manner. The gases evolved consisted chiefly of ammonia and nitrogen, similar to the case of TAGN alone. Thus, it appears that the acetate groups are critical in the interaction between TAGN and CA in which N_2O is produced in the CAB.

Further experiments were performed to determine if ammonia alone is sufficient to react with cellulose acetate and produce N_2O . An ammonium salt (NH_4HCO_3 , which volatilizes at the $220^\circ C$ used in these thermal decomposition to yield NH_3 and CO_2) was mixed with cellulose acetate and treated as above. No N_2O was obtained. Conversely, a mixture of TAGN and acetic acid was prepared to determine if acetic acid is sufficient to react with TAGN and cause the formation of N_2O . Again, none was seen, the chief products being those of the individual components alone.

From these results we can conclude that the acetate functional group of cellulose acetate is essential for the reaction with TAGN to produce N_2O . It is not yet certain in what manner the TAGN molecule reacts with CA in this decomposition. Further experiments are planned to determine this as well as whether the reactions occur in the gas or condensed phases.

IV. FTIR RESULTS

The infrared experiments were performed (a) in order to characterize the solid residue from the TAGN decomposition-MS experiments and (b) to determine any difference in a pure sample of TAGN and a batch of pink TAGN which was prepared at ICT. By analyzing both the solid and gaseous products from the MS thermal treatment, the decomposition mechanism of TAGN under the conditions used could be better elucidated.

TAGN samples were heated for MS decomposition studies as described above. Since NH_3 is the chief decomposition gas it was quite logical to suspect that the less substituted guanidine nitrates might be formed in the decomposition of TAGN. Thus, the spectra of diaminoguanidine nitrate (DAGN), aminoguanidine nitrate (AGN), and guanidine nitrate (GN) as well as TAGN were obtained as reference compounds. These are shown in Figure 1 and the absorption frequencies and assignments of the major bands are shown in Table 2. The infrared spectra and band assignments for TAGN had previously been reported by Brill.⁷ Some features of the reference spectra are worth noting. As the NH groups are removed from TAGN, the bands due to NH asymmetric stretch begin to broaden. The C-N band at 1685 in TAGN (with partial double bond character) shifts to lower frequency with fewer NH groups.

The N-N band of medium intensity at 1129 cm^{-1} in the TAGN spectrum has a significantly lower relative intensity in DAGN and is barely discernable in AGN. This is expected, based on the structure of these compounds. The N-N band is fairly weak, even in TAGN which has three N-N bonds. DAGN has one less N-N bond and the band is weaker than in TAGN. In AGN (only one N-N bond) the band is barely discernable. The other prominent bands in TAGN are the nitrate bands, the strongest of which is at 1384 cm^{-1} and a small but sharp band at 825 cm^{-1} . These bands were identified from a pure sample of KNO_3 and appear to be stronger in the decomposition products, relative to TAGN.




Figure 1. Infrared Spectra of the Tri-, Di-, Mono-Amino and Unsubstituted Guanidine Nitrates

Three samples were chosen from the MS experiments for analysis by IR, to determine what differences might be seen relative to the pure TAGN. Two samples were solid residues, obtained by heating TAGN at 210°C and 220°C for 15 minutes. The third sample consisted of a powder which was initially only slightly off-white in color and which was found condensed on the side of a glass tube in a small area where the glass was not completely wrapped with heating tape. This condensed material was removed from the tube (inadvertantly with a metal spatula) and saved in a glass vial. Two days later it was noticed that the material was brilliant red and was therefore of significant interest. The infrared spectra of this material is shown in Figure 2, along with that of DAGN; the similarity is striking and shows that the condensate consists chiefly of DAGN. The pink color is due either to an impurity or decomposition product; pure DAGN is a white crystalline material.

The solid decomposition residues are not so easily identified although trends in their spectra suggest general changes in the structure of the TAGN. The TAGN heated to 210 was originally light pink and yielded a gummy residue which was medium pink and whose spectrum is seen in Figure 3. A pure sample of TAGN was heated to 220°C and yielded a residue of similar texture to that at 220°C, but was only light pink in color. The absence of the N-N band suggest that most of these bonds have been broken; the broad and featureless NH bands also indicate increased decomposition. The residue probably consists of a mixture of products and thus, identification is difficult. However, it appears likely that TAGN forms such compounds in its early decomposition.

Table 2. Major Infrared Absorption Band Assignments for the Tri-, Di-, Mono-Amino and Unsubstituted Guanidine Nitrates

IR -----	NH ₂ -----	N-C-N -----	N-N -----
<u>Sample:</u>			
TAGN	3214-3319	1685	1129
DAGN	3216-3353	1682	1127
AGN	3263-3452	1671/1657	1120
GN	3202-3448	1666	----
<u>Heated:</u>			
Red Condensate	3213-3319	1684	1128
TAGN Residue (210°C)	3215-3307	1660	----
TAGN Residue (220°C)	3157-3385	1654	1130
<u>Unheated:</u>			
Red Crystals from			
Recrystall. Solvent	3212-3319	1685	1128
Pink TAGN	3213-3343	1685	1128

Note: The nitrate bands have the same frequency for each sample and are at 1385 cm⁻¹ and 825 cm⁻¹.




Figure 2. Comparison of the Infrared Spectra of a TAGN Decomposition/Condensate Product and DAGN




Figure 3. Infrared Spectra of the Solid Decomposition Products of TAGN Heated to 210-220°C

The next set of IR samples were analyzed to determine if any difference in the spectra of pink or pure TAGN samples could be determined. Previous researchers had detected no differences but it was decided to try again. A medium pink sample of TAGN (the pinkest available) was chosen, but was still damp from the mother liquor. Unfortunately, when this sample was dried for IR analysis, most of the pink color was also removed. A similar effect had also been previously reported.⁸ The spectrum was similar to that of TAGN and is not shown.

It was known that the pink crystals can be washed with deionized water and the pink color removed. TAGN crystals appear as hollow cylinders when viewed under a microscope. It is believed that much of the pink color is due to liquid trapped in the hollow spaces of the cylinder.⁹ At ICT researchers had also prepared a sample of crystals which, when washed, turned the deionized water a pink-orange color. This wash-water was collected and concentrated (under vacuum-no heat) for IR analysis. In the first attempt the sample was extracted into methylene chloride (which then turned pink) and evaporated to dryness. However, the resulting crystals were white and the spectrum was identical to TAGN (not shown).

Another attempt was made using this recrystallization liquor in which the water was again removed under vacuum without heat. After several hours under vacuum the solution remained clear, but turned a beautiful red color. The water was completely evaporated and the resulting crystals were run as KBr pellets and the results are shown in Figure 4a. The only difference between this and the TAGN spectra (Figure 4b) is the stronger nitrate band of the former. This might suggest that the sample becomes enriched in nitrate. If so, unlike the decomposition spectra discussed above, the larger nitrate band is not accompanied by any change in the TAG (triaminoguanidine) portion of the molecule; the band positions are similar to those of TAGN (Table 1). Thus, the pink color could be due to some nitrate complex (possibly a metal nitrate) present in TAGN which, except for the nitrate band, does not absorb significantly in the IR.

Previous researchers have speculated that the pink color is due to the formation of conjugated double-bonded complexes which form from TAGN after the loss of nitrate, and that the latter is washed away in the recrystallization fluid.⁸ However, the nitrate band in the spectra of the pink and red crystals described above does not support this. Also, if such conjugated TAG-like complexes did form, they would expect to be at least weakly IR absorbing, being C=N and N=N type bands. Thus, in such deeply red crystals as used in this experiment one might expect to see at least minor changes in the IR spectrum. None were observed, except for the nitrate band intensity, as indicated above. Whether the stronger nitrate band is due to an increased concentration of nitrate or simply to crystal effects is not yet known.

V. ATOMIC ABSORPTION ANALYSIS

Since it seemed possible that the pink (red) color of some the samples might be related to the presence of metal, atomic absorption spectroscopy (AAS) analyses were run on several of the samples.

The metals determined were those which are most common: Fe, Cu, Ni, Zn, Cd and Cr. The level of all of these was below their detection limits. The

likelihood of contact of the sample with any other metal is slim and thus, it seems doubtful that any residual metal complex impurity was the cause of the pink color.




Figure 4. The Infrared Spectra of: (a) Deep Red Crystals Obtained by Vacuum Drying the Recrystallization Water and (b) TAGN

VI. C, H, N, AND O ANALYSIS

Elemental analysis was performed on duplicate samples of pure TAGN, pink TAGN and crystals which formed from the recrystallization solvent (all samples were dried under vacuum to ensure that any residual solvent was removed). Samples of the residue obtained by heating TAGN to 210 or 220°C for 15 min were also analyzed. Duplicate samples of the pure TAGN residue were prepared. Single samples of pink TAGN and pink TAGN which had been washed until it became white were also analyzed, as well as a single sample of the red-colored material which had condensed on the walls of the test tube while heating a pure sample. The results of these analyses are shown in Tables 3 and 4. In the case of the duplicated samples the average of the two results and the standard deviation is given (Table 2). The delta (Δ) value is the difference between the theoretical value for TAGN and the analytical value; the % value is the % change from the theoretical values for a sample of pure TAGN (Table 4). For the pure TAGN sample Δ gives an estimate of the accuracy of the analysis. It can be seen that the C and H values are more accurate than are those of nitrogen; those of oxygen are obtained by subtracting the sum of the others from 100 and are the least accurate. Results for nitrogen with the instrument used in this work are consistently less accurate than for carbon or hydrogen.¹⁰ Whether this accounts for the discrepancy between the theoretical and unheated, pure TAGN in Table 4 is unclear. Thus, there may be some minor impurity/decomposition within the parent material.

Unfortunately, no significant difference was seen between either the pink TAGN crystals or the crystals obtained from the recrystallization fluid. However, the latter were only very slightly pink and are not the brilliant red crystals on which the IR analysis was made.

The results for the decomposition residue and, to a lesser extent, the condensate show that these samples are enriched in C and O₂ and have less H₂ and N₂ present, relative to TAGN. This is in agreement with the MS results which have indicated that the chief products are N₂ and NH₃, and that there are copious amounts of both formed. Other gases (containing C and O₂) are found in only small quantities at high temperature and/or longer heating durations. Since the only source of oxygen in the TAGN molecule is the HNO₃ group, the enrichment of O₂ supports the IR result (formation of DAGN and AGN as the sample decomposes) that decomposed samples are enriched in nitrate. Any enrichment of nitrogen due to the nitrate is negated by the large loss of N₂ and NH₃ and thus the percent nitrogen in the decomposed samples is lower than that of TAGN. It should be noted here again that the condensate and pink TAGN were only pale pink in color and were not the samples for which the IR results were obtained.

VII. DIFFERENTIAL SCANNING CALORIMETRY

In the DSC at 10°C/min, the exothermic decomposition of TAGN begins immediately after the melting point and reaches its maximum at about 232°C (Figure 5). A second, slightly sharper exotherm is observed at 278°C, with a smaller and more variable exotherm (265°C) occurring between the 2 larger exotherms. The first exotherm (just after the melting point) is the one associated with the reactions studied in the mass spectrometer (mainly N₂ and NH₃ evolution). This is evidenced by the fact that when the residue from the MS experiments is run in the DSC, the first exotherm normally seen in TAGN is

not present in the curve for the residue (Figure 6), and only the second major exotherm is seen. In addition, this second peak occurs at the same temperature as that found when DAGN is decomposed in the DSC (Figure 6b). This lends further support to the MS, FTIR and elemental analyses that DAGN is formed from mild decomposition of TAGN.

Table 3. Elemental Analysis of TAGN and the Residue/Condensate from the MS Experiments; the Theoretical Value for Pure/Undecomposed TAGN is Given as a Reference

Sample	C	H	N	O 100-(C+N+H)
TAGN (Theoretical)	7.18	5.42	58.64	28.73
<u>Unheated:</u>				
TAGN (Pure)	7.11 ± .05 Δ = - 0.07	5.45 ± .01 Δ = 0.03	55.75 ± .89 Δ = - 2.89	31.69 ± .83 Δ = - 2.96
TAGN (Pink)	7.20 ± .02 Δ = 0.02	5.46 ± .03 Δ = 0.04	55.44 ± .82 Δ = - 3.20	31.88 ± .85 Δ = 3.15
Crystals from Recrystallization Solvent	7.14 ± .01 Δ = - 0.04	5.51 ± .01 Δ = 0.09	55.77 ± .71 Δ = - 2.87	31.57 ± .71 Δ = 2.84
<u>Heated:</u>				
Pure TAGN Residue	9.63 ± .20 Δ = 2.45	4.89 ± .02 Δ = - 0.50	42.88 ± .57 Δ = - 16.33	42.59 ± .38 Δ = 13.86
Washed Pink TAGN Residue	9.78 Δ = 36.20	4.51 Δ = - 0.91	41.49 Δ = - 17.15	44.22 Δ = 15.49
Pink TAGN Residue	11.99 Δ = 4.80	4.40 Δ = - 1.02	45.00 Δ = - 13.64	38.61 Δ = 9.88
Condensate from Pure TAGN	8.83 Δ = 1.65	4.94 Δ = - 0.48	49.84 Δ = - 8.80	36.39 Δ = 7.66

Note: Values with error bars are the average of two measurements.
Delta (Δ) represents the difference between the experimental and theoretical values.




Figure 5. Differential Scanning Calorimetry Analysis of TAGN




Figure 6. Differential Scanning Calorimetry Analysis of (a) the Solid Decomposition Residue of TAGN and (b) DAGN

Table 4. Percent Change in Elemental Analysis from the Theoretical Values for TAGN. A positive sign indicates a value greater than the theoretical; a negative value indicate a value less than the theoretical.

Sample	C	H	N	O
TAGN (Theoretical)	7.18	5.42	58.64	28.73
Percent Difference from Theoretical Value:				
<u>Unheated:</u>				
TAGN (Pure)	-0.9	0.5	4.9	-10.3
TAGN (Pink)	0.2	0.7	5.4	10.9
Crystals from Recrystallization Solvent	-0.5	1.6	-4.9	9.8
<u>Heated:</u>				
Pure TAGN Residue	+34.1	-9.8	-27.8	+48.
Washed Pink TAGN Residue	+36.2	-16.8	-17.2	+54.9
Pink TAGN Residue	+66.8	-18.8	-23.2	+34.1
Condensate	+22.9	-8.8	-15.0	+26.6

TAGN and RDX alone give what might be described as a "controlled reaction" (peaks are roughly Gaussian in shape) and occur over a range of several minutes. In the case of RDX (Figure 7) the exothermic reaction begins just after melting (at about 210) and peaks at about 235°C. However, when TAGN is mixed with RDX the exotherm begins at about 210 and reaches its maximum almost immediately so that the curve resembles a spike more than a peak. The DSC of TAGN alone is shown again as a reference for which to compare temperature shifts. This result had previously been observed in another laboratory using a different model of DSC.¹¹ Since variations in design (different sample containers, variations in purge flow over sample, etc.) can result in differences in pressure and atmosphere composition of the sample surroundings, results on this DSC were obtained for comparison.

The MS results indicate that the initial decomposition at mild temperatures (190-220°C) is due to evolution of NH₃ and N₂ and not to loss of HNO₃. The enrichment of C and O₂ in the residue (and corresponding loss of N₂ and H₂) as well as the increase in nitrate bands in the residue as seen by IR support this. It is interesting to note that the residue is typically a light to medium pink color (the pink color increasing with the degree of decomposition) and that the sublimate was intensely red. If these pink decomposition products are related to the pink color seen in impure TAGN, then these results also do not support the hypothesis that the impurity in pink TAGN forms by initial cleavage and loss of HNO₃. Each of these samples showed an enrichment of nitrate.




Figure 7. DSC Analysis of (a) RDX and (b) a 1:1 Mixture of RDX and TAGN

VIII. THIN LAYER CHROMATOGRAPHY

It is desirable to be able to separate the decomposition products of TAGN and a partial separation has recently been achieved. Preliminary attempts to separate the components using normal and both C-18 and amino-substituted reverse phase HPLC failed and thus the faster TLC method was used to select appropriate conditions for the separation. Standards used in the separation are the same as those used as IR references, namely DAGN, AGN, and GN.

A chromatogram showing the separation of two decomposition residues and the standards is given in Figure 8. It is seen that TAGN is the least retained by the plate, followed by DAGN + AGN; GN travels only a small distance with the solvent and is found on the lower portion of the TLC plate. The residue from TAGN thermal decomposition consists of a large amount of DAGN, smaller quantities of AGN and TAGN and no detectable GN. In addition, three components (at least) are present which elute between AGN and DAGN, one of which is quite streaked, possibly due to a significant difference in polarity or functional groups relative to the other samples so that it does not chromatograph as nicely as the others. It is also quite probable that the unknown spots are due to components which are intermediate in size between AGN and DAGN. Considering the structure of TAGN, this may indicate that the bonds between C and N have been broken in these cases, because if only N-N bonds are broken, most probably DAGN, AGN or GN would be formed. Infrared analysis of the spots was attempted. The material from several runs was pooled and extracted and analyzed on a salt plate. Unfortunately, not enough sample was recovered to obtain a spectrum. Reflectance or microsampling attachments were not available but might enable an identification of the sample.

The TLC results support those from the MS and CHN and O analyses, since DAGN and AGN shown here to be present in the residue would be formed from evolution of NH_3 and one would expect a relative loss of N_2 and enrichment of C. Also, in the infrared spectra of DAGN and AGN the nitrate band is larger relative to the C-N band; their presence or seen in the TLC results supports the finding of a larger nitrate band (relative to the C-N band) in the residue than in the TAGN.

IX. CONCLUSIONS

The results of the thermal decomposition of TAGN are as follows:

1. Measurement of the evolved gases by MS has indicated that TAGN loses NH_3 and N_2 as its early decomposition products.
2. The MS results were supported by C, H, N, and O analysis of the residue; it was found to be enriched in carbon and oxygen and showed a loss of nitrogen and hydrogen, compared to unheated TAGN.
3. Infrared analysis indicated that the residue from TAGN heated between 210 and 220°C is probably a mixture consisting of DAGN and AGN, based on band frequencies and relative intensities. A substance which condensed on the walls of the container during heating was identified as DAGN.
4. TLC analysis of the TAGN residue also indicated the presence of DAGN and AGN, as well as at least three other unknown products.

5. DSC analysis showed that the NH_3 and N_2 evolution is the first major exothermic reaction in TAGN decomposition.

In addition, a pink TAGN was investigated. The FTIR analysis indicated that the TAG portion of the molecule had not undergone decomposition and the only difference between the pink TAGN and pure TAGN was the greater intensity of the nitrate band in the pink sample. A sample of deep red TAGN crystals was prepared and its spectrum was also identical to TAGN with the exception of an even greater nitrate band intensity (relative) than was seen in the pink species. The source of this strong nitrate band is under investigation.

In conclusion, the results of MS, IR, TLC, and elemental analyses agree and indicate that TAGN decomposes under the conditions used to yield mainly NH_3 and N_2 and a residue containing DAGN, AGN and other products. No evidence for GN formation was obtained. DSC results show that the NH_3 and N_2 evolution is the first exothermic step in the decomposition of TAGN. Pink TAGN is possibly related to an enrichment of nitrate.

REFERENCES

1. H.W. Voight and J.P. Picard, "RDX/TAGN Propellants of Increased Heat Stability and Safe Pressure Exponent," Third International Gun Propellant Symposium, Vol. IV, pp. 248-267, 1984.
2. O.K. Heiney, "Nitramine Gun Propellant for 30MM Gau-8 Application," Third International Gun Propellant Symposium, Vol. IV, pp. 209-225, 1984.
3. N.F. Stanley, "Energetic, Cool-Burning Gun Propellants," Air Force Armament Laboratory, AFATL-TR-78-136, September 1979.
4. J.E. Flanagan, "Advanced Gun Propellant for GAU-8", Proceedings of 11th JANNAF Combustion Meeting, CPIA Publ. 261, Vol. I, pp. 285-291, December 1974.
5. F. Schedlbauer, "Investigation of the Combustion Behavior of LOVA-Propellants," ADPA Proceedings, Long Beach CA, 1986.
6. D. Muller, Fraunhofer Institute (ICT), West Germany, personal communication.
7. Y. Oyumi and T.B. Brill, "Thermal Decomposition of Energetic Materials. 6. Solid-Phase Transitions and the Decomposition of 1,2,3-Triaminoquanidinium Nitrate," J. Phys. Chem., Vol. 89, pp. 4325-4329, 1985.
8. C.W. Fong, "The Formation of Colored Impurities in Triaminoguanidine Nitrate and Related Incompatibility Problems in Gun Propellants," Air Force Armament Laboratory, AFATL-TR-81-101, August 1982.
9. A.J. Bracuti, "The Crystal Structure Determination of Triaminoguanidine Nitrate," ARDC, ARLCD-TR-78050, 1979.
10. F. Volk, Fraunhofer Institute fur Treib und Explosivstoffe, ICT, Karlsruhe, West Germany, private communication.
11. P.J. Kaste and L.J. Decker, BRL Technical Report in progress.

DISTRIBUTION LIST

<u>No. Of Copies</u>	<u>Organization</u>	<u>No. Of Copies</u>	<u>Organization</u>
12	Administrator Defense Technical Info Center ATTN: DTIC-DDA Cameron Station Alexandria, VA 22304-6145	1	Commander US Army Aviation Systems Command ATTN: AMSAV-DACL 4300 Goodfellow Blvd. St. Louis, MO 63120-1798
1	HQ DA (SARD-TR) Washington, DC 20310	1	Director US Army Aviation Research and Technology Activity Ames Research Center Moffett Field, CA 94035-1099
1	Commander US Army Materiel Command ATTN: AMCDRA-ST 5001 Eisenhower Avenue Alexandria, VA 22333-0001	4	Commander US Army Research Office ATTN: R. Ghirardelli D. Mann R. Singleton R. Shaw P.O. Box 12211 Research Triangle Park, NC 27709-2211
1	Commander US Army Laboratory Command ATTN: AMSLC-TD Adelphi, MD 20783-1145	1	Commander US Army Communications - Electronics Command ATTN: AMSEL-ED Fort Monmouth, NJ 07703
1	Commander Armament R&D Center US Army AMCCOM ATTN: SMCAR-MSI Picatinny Arsenal, NJ 07806-5000	2	Commander Armament R&D Center US Army AMCCOM ATTN: SMCAR-LCA-G, D.S. Downs J.A. Lannon Dover, NJ 07801
1	Commander Armament R&D Center US Army AMCCOM ATTN: SMCAR-TDC Picatinny Arsenal, NJ 07806-5000	1	Commander Armament R&D Center US Army AMCCOM ATTN: SMCAR-LC-G, L. Harris Dover, NJ 07801
1	Director Benet Weapons Laboratory Armament R&D Center US Army AMCCOM ATTN: SMCAR-LCB-TL Watervliet, NY 12189-4050		
1	Commander US Army Armament, Munitions and Chemical Command ATTN: SMCAR-ESP-L Rock Island, IL 61299-7300		

DISTRIBUTION LIST

<u>No. Of Copies</u>	<u>Organization</u>	<u>No. Of Copies</u>	<u>Organization</u>
1	Commander Armament R&D Center US Army AMCCOM ATTN: SMCAR-SCA-T, L. Stiefel Dover, NJ 07801	1	Office of Naval Research Department of the Navy ATTN: R.S. Miller, Code 432 800 N. Quincy Street Arlington, VA 22217
2	Commander US Army Missile Command ATTN: AMSMI-RD AMSMI-AS Redstone Arsenal, AL 35898-5000	1	Commander Naval Air Systems Command ATTN: J. Ramnarace, AIR-54111C Washington, DC 20360
2	Commander US Army Missile Command ATTN: AMSMI-RK, D.J. Ifshin W. Wharton Redstone Arsenal, AL 35898	2	Commander Naval Ordnance Station ATTN: C. Irish P.L. Stang, Code 515 Indian Head, MD 20640
1	Commander US Army Missile Command ATTN: AMSMI-RKA, A.R. Maykut Redstone Arsenal, AL 35898-5249	1	Commander Naval Surface Weapons Center ATTN: J.L. East, Jr., G-23 Dahlgren, VA 22448-5000
1	Commander US Army Tank Automotive Cmd ATTN: AMSTA-DI Warren, MI 48090	2	Commander Naval Surface Weapons Center ATTN: R. Bernecker, R-13 G.B. Wilmot, R-16 Silver Spring, MD 20902-5000
1	Director US Army TRADOC Analysis Cmd ATTN: ATAA-SL White Sands Missile Range, NM 88002-5502	5	Commander Naval Research Laboratory ATTN: M.C. Lin J. McDonald E. Oran J. Shnur R.J. Doyle, Code 6110 Washington, DC 20375
1	Commandant US Army Infantry School ATTN: ATSH-CD-CSO-OR Fort Benning, GA 31905-5400	1	Commanding Officer Naval Underwater Systems Center Weapons Dept. ATTN: R.S. Lazar/Code 36301 Newport, RI 02840
1	Commander US Army Development and Employment Agency ATTN: MODE-ORO Fort Lewis, WA 98433-5000	1	Superintendent Naval Postgraduate School Dept. of Aeronautics ATTN: D.W. Netzer Monterey, CA 93940

DISTRIBUTION LIST

<u>No. Of Copies</u>	<u>Organization</u>	<u>No. Of Copies</u>	<u>Organization</u>
4	AFRPL/DY, Stop 24 ATTN: R. Corley R. Geisler J. Levine D. Weaver Edwards AFB, CA 93523-5000	1	Applied Combustion Technology, Inc. ATTN: A.M. Varney P.O. Box 17885 Orlando, FL 32860
1	AFRPL/MKPB, Stop 24 ATTN: B. Goshgarian Edwards AFB, CA 93523-5000	2	Applied Mechanics Reviews The American Society of Mechanical Engineers ATTN: R.E. White A.B. Wenzel 345 E. 47th Street New York, NY 10017
1	AFOSR ATTN: J.M. Tishkoff Bolling Air Force Base Washington, DC 20332	1	Atlantic Research Corp. ATTN: M.K. King 5390 Cherokee Avenue Alexandria, VA 22314
1	Air Force Armament Laboratory ATTN: AFATL/DLODL Eglin AFB, FL 32542-5000	1	Atlantic Research Corp. ATTN: R.H.W. Waesche 7511 Wellington Road Gainesville, VA 22065
1	AFWL/SUL Kirtland AFB, NM 87117	1	AVCO Everett Rsch. Lab. Div. ATTN: D. Stickler 2385 Revere Beach Parkway Everett, MA 02149
1	NASA Langley Research Center Langley Station ATTN: G.B. Northam/MS 168 Hampton, VA 23365	1	Battelle Memorial Institute Tactical Technology Center ATTN: J. Huggins 505 King Avenue Columbus, OH 43201
4	National Bureau of Standards ATTN: J. Hastie M. Jacox T. Kashiwagi H. Semerjian US Department of Commerce Washington, DC 20234	1	Cohen Professional Services ATTN: N.S. Cohen 141 Channing Street Redlands, CA 92373
1	OSD/SDIO/UST ATTN: L.H. Caveny Pentagon Washington, DC 20301-7100	1	Exxon Research & Eng. Co. ATTN: A. Dean Route 22E Annandale, NJ 08801
1	Aerojet Solid Propulsion Co. ATTN: P. Micheli Sacramento, CA 95813		

DISTRIBUTION LIST

<u>No. Of Copies</u>	<u>Organization</u>	<u>No. Of Copies</u>	<u>Organization</u>
1	Ford Aerospace and Communications Corp. DIVAD Division Div. Hq., Irvine ATTN: D. Williams Main Street & Ford Road Newport Beach, CA 92663	1	Honeywell, Inc. Government and Aerospace Products ATTN: D.E. Broden/ MS MN50-2000 600 2nd Street NE Hopkins, MN 55343
1	General Applied Science Laboratories, Inc. 77 Raynor Avenue Ronkonkama, NY 11779-6649	1	IBM Corporation ATTN: A.C. Tam Research Division 5600 Cottle Road San Jose, CA 95193
1	General Electric Armament & Electrical Systems ATTN: M.J. Bulman Lakeside Avenue Burlington, VT 05401	1	IIT Research Institute ATTN: R.F. Remaly 10 West 35th Street Chicago, IL 60616
1	General Electric Company 2352 Jade Lane Schenectady, NY 12309	2	Director Lawrence Livermore National Laboratory ATTN: C. Westbrook M. Costantino P.O. Box 808 Livermore, CA 94550
1	General Electric Ordnance Systems ATTN: J. Mandzy 100 Plastics Avenue Pittsfield, MA 01203	1	Lockheed Missiles & Space Co. ATTN: George Lo 3251 Hanover Street Dept. 52-35/B204/2 Palo Alto, CA 94304
2	General Motors Rsch Labs Physics Department ATTN: T. Sloan R. Teets Warren, MI 48090	1	Los Alamos National Lab ATTN: B. Nichols T7, MS-B284 P.O. Box 1663 Los Alamos, NM 87545
2	Hercules, Inc. Allegany Ballistics Lab. ATTN: R.R. Miller E.A. Yount P.O. Box 210 Cumberland, MD 21501	1	National Science Foundation ATTN: A.B. Harvey Washington, DC 20550
1	Hercules, Inc. Bacchus Works ATTN: K.P. McCarty P.O. Box 98 Magna, UT 84044	1	Olin Corporation Smokeless Powder Operations ATTN: V. McDonald P.O. Box 222 St. Marks, FL 32355

DISTRIBUTION LIST

<u>No. Of Copies</u>	<u>Organization</u>	<u>No. Of Copies</u>	<u>Organization</u>
1	Paul Gough Associates, Inc. ATTN: P.S. Gough 1048 South Street Portsmouth, NH 03801	1	Stevens Institute of Tech. Davidson Laboratory ATTN: R. McAlevy, III Hoboken, NJ 07030
2	Princeton Combustion Research Laboratories, Inc. ATTN: M. Summerfield N.A. Messina 475 US Highway One Monmouth Junction, NJ 08852	1	Textron, Inc. Bell Aerospace Co. Division ATTN: T.M. Fenger P.O. Box 1 Buffalo, NY 14240
1	Hughes Aircraft Company ATTN: T.E. Ward 8433 Fallbrook Avenue Canoga Park, CA 91303	1	Thiokol Corporation Elkton Division ATTN: W.N. Brundige P.O. Box 241 Elkton, MD 21921
1	Rockwell International Corp. Rocketdyne Division ATTN: J.E. Flanagan/HB02 6633 Canoga Avenue Canoga Park, CA 91304	1	Thiokol Corporation Huntsville Division ATTN: R. Glick Huntsville, AL 35807
4	Sandia National Laboratories Combustion Sciences Dept. ATTN: R. Cattolica S. Johnston P. Mattern D. Stephenson Livermore, CA 94550	3	Thiokol Corporation Wasatch Division ATTN: S.J. Bennett P.O. Box 524 Brigham City, UT 84302
1	Science Applications, Inc. ATTN: R.B. Edelman 23146 Cumorah Crest Woodland Hills, CA 91364	1	TRW ATTN: M.S. Chou MSR1-1016 1 Parke Redondo Beach, CA 90278
1	Science Applications, Inc. ATTN: H.S. Pergament 1100 State Road, Bldg. N Princeton, NJ 08540	1	United Technologies ATTN: A.C. Eckbreth East Hartford, CT 06108
3	SRI International ATTN: G. Smith D. Crosley D. Golden 333 Ravenswood Avenue Menlo Park, CA 94025	3	United Technologies Corp. Chemical Systems Division ATTN: R.S. Brown T.D. Myers (2 copies) P.O. Box 50015 San Jose, CA 95150-0015

DISTRIBUTION LIST

<u>No. Of Copies</u>	<u>Organization</u>	<u>No. Of Copies</u>	<u>Organization</u>
1	Universal Propulsion Company ATTN: H.J. McSpadden Black Canyon Stage 1 Box 1140 Phoenix, AZ 85029	2	University of Southern California Dept. of Chemistry ATTN: S. Benson C. Wittig Los Angeles, CA 90007
1	Veritay Technology, Inc. ATTN: E.B. Fisher 4845 Millersport Highway P.O. Box 305 East Amherst, NY 14051-0305	1	Case Western Reserve Univ. Div. of Aerospace Sciences ATTN: J. Tien Cleveland, OH 44135
1	Brigham Young University Dept. of Chemical Engineering ATTN: M.W. Beckstead Provo, UT 84601	1	Cornell University Department of Chemistry ATTN: T.A. Cool Baker Laboratory Ithaca, NY 14853
1	California Institute of Tech. Jet Propulsion Laboratory ATTN: MS 125/159 4800 Oak Grove Drive Pasadena, CA 91103	1	Univ. of Dayton Rsch Inst. ATTN: D. Campbell AFRPL/PAP Stop 24 Edwards AFB, CA 93523
1	California Institute of Technology ATTN: F.E.C. Culick/ MC 301-46 204 Karman Lab. Pasadena, CA 91125	1	University of Florida Dept. of Chemistry ATTN: J. Winefordner Gainesville, FL 32611
1	University of California, Berkeley Mechanical Engineering Dept. ATTN: J. Daily Berkeley, CA 94720	3	Georgia Institute of Technology School of Aerospace Engineering ATTN: E. Price W.C. Strahle B.T. Zinn Atlanta, GA 30332
1	University of California Los Alamos Scientific Lab. P.O. Box 1663, Mail Stop B216 Los Alamos, NM 87545	1	University of Illinois Dept. of Mech. Eng. ATTN: H. Krier 144MEB, 1206 W. Green St. Urbana, IL 61801
2	University of California, Santa Barbara Quantum Institute ATTN: K. Schofield M. Steinberg Santa Barbara, CA 93106	1	Johns Hopkins University/APL Chemical Propulsion Information Agency ATTN: T.W. Christian Johns Hopkins Road Laurel, MD 20707

DISTRIBUTION LIST

<u>No. Of Copies</u>	<u>Organization</u>	<u>No. Of Copies</u>	<u>Organization</u>
1	University of Michigan Gas Dynamics Lab Aerospace Engineering Bldg. ATTN: G.M. Faeth Ann Arbor, MI 48109-2140	1	Purdue University Department of Chemistry ATTN: E. Grant West Lafayette, IN 47906
1	University of Minnesota Dept. of Mechanical Engineering ATTN: E. Fletcher Minneapolis, MN 55455	2	Purdue University School of Mechanical Engineering ATTN: N.M. Laurendeau S.N.B. Murthy TSPC Chaffee Hall West Lafayette, IN 47906
3	Pennsylvania State University Applied Research Laboratory ATTN: K.K. Kuo H. Palmer M. Micci University Park, PA 16802	1	Rensselaer Polytechnic Inst. Dept. of Chemical Engineering ATTN: A. Fontijn Troy, NY 12181
1	Pennsylvania State University Dept. of Mechanical Engineering ATTN: V. Yang University Park, PA 16802	1	Stanford University Dept. of Mechanical Engineering ATTN: R. Hanson Stanford, CA 94305
1	Polytechnic Institute of NY Graduate Center ATTN: S. Lederman Route 110 Farmingdale, NY 11735	1	University of Texas Dept. of Chemistry ATTN: W. Gardiner Austin, TX 78712
2	Princeton University Forrestal Campus Library ATTN: K. Brezinsky I. Glassman P.O. Box 710 Princeton, NJ 08540	1	University of Utah Dept. of Chemical Engineering ATTN: G. Flandro Salt Lake City, UT 84112
1	Princeton University MAE Dept. ATTN: F.A. Williams Princeton, NJ 08544	1	Virginia Polytechnic Institute and State University ATTN: J.A. Schetz Blacksburg, VA 24061
1	Purdue University School of Aeronautics and Astronautics ATTN: J.R. Osborn Grissom Hall West Lafayette, IN 47906	1	Commandant USAFAS ATTN: ATSF-TSM-CN Fort Sill, OK 73503-5600
		1	F.J. Seiler Research Lab (AFSC) ATTN: S.A. Shakelford USAF Academy, CO 80840-6528

DISTRIBUTION LIST

<u>No. Of</u> <u>Copies</u>	<u>Organization</u>
--------------------------------	---------------------

Aberdeen Proving Ground

Dir, USAMSAA

ATTN: AMXSY-D

AMXSY-MP, H. Cohen

Cdr, USATECOM

ATTN: AMSTE-TO-F

Cdr, CRDEC, AMCCOM

ATTN: SMCCR-RSP-A

SMCCR-MU

SMCCR-SPS-IL

USER EVALUATION SHEET/CHANGE OF ADDRESS

This Laboratory undertakes a continuing effort to improve the quality of the reports it publishes. Your comments/answers to the items/questions below will aid us in our efforts.

1. BRL Report Number _____ Date of Report _____
2. Date Report Received _____
3. Does this report satisfy a need? (Comment on purpose, related project, or other area of interest for which the report will be used.) _____

4. How specifically, is the report being used? (Information source, design data, procedure, source of ideas, etc.) _____

5. Has the information in this report led to any quantitative savings as far as man-hours or dollars saved, operating costs avoided or efficiencies achieved, etc? If so, please elaborate. _____

6. General Comments. What do you think should be changed to improve future reports? (Indicate changes to organization, technical content, format, etc.) _____

CURRENT
ADDRESS

Name

Organization

Address

City, State, Zip

7. If indicating a Change of Address or Address Correction, please provide the New or Correct Address in Block 6 above and the Old or Incorrect address below.

OLD
ADDRESS

Name

Organization

Address

City, State, Zip

(Remove this sheet, fold as indicated, staple or tape closed, and mail.)

----- FOLD HERE -----

Director
U.S. Army Ballistic Research Laboratory
ATTN: SLCBR-DD-T
Aberdeen Proving Ground, MD 21005-5066



NO POSTAGE
NECESSARY
IF MAILED
IN THE
UNITED STATES

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE, \$300

BUSINESS REPLY MAIL
FIRST CLASS PERMIT NO 12062 WASHINGTON, DC
POSTAGE WILL BE PAID BY DEPARTMENT OF THE ARMY

Director
U.S. Army Ballistic Research Laboratory
ATTN: SLCBR-DD-T
Aberdeen Proving Ground, MD 21005-9989



----- FOLD HERE -----

U238259

DA Label 18-1, Sep 83
Edition of Oct 74 will be used until exhausted.

DEPARTMENT OF THE ARMY

US ARMY BALLISTIC RESEARCH LAB

ATTN: SLCBR-DB-T (NEI)
ABERDEEN PROVING GROUND, MD.

21005-5006

OFFICIAL BUSINESS

PENALTY FOR PRIVATE USE \$300

1

Superintendent
Naval Postgraduate School
Dept. of Aeronautics
ATTN: D.W. Netzer
Monterey, CA 93940